

-No. The standard test method is only suitable for those powders that will flow unaided through the specified apparatus. For those powders difficult to pass through a standard 2.5 or 5.0 mm orifice, there are following test methods:

- Scott volumeter method
- Vibration hall flowmeter funnel method
- Arnold meter method